



Veneer Black Locust steamed 0.56 mm

Item No. 01-000015



Description

The robinia tree originates from eastern North America. It owes its name to a French court gardener in Paris, Jean Robin, who brought the tree to France in the 17th century. The American name is "Black Locust", which translates as "black grasshopper". The species is so called because the dried legumes remain on the tree for a long time after the leaves have fallen and are strongly reminiscent of locusts.

For some years now, however, people have been reflecting on the outstanding qualities of the robinia, and there are now many approaches to increasingly consider the robinia in the afforestation of areas, with the declared aim of producing wood. All in all, with almost 2 million hectares (as of May 2001), Robinia ranks third worldwide among deciduous trees from plantations.

Trade names and other names

Abbreviation DIN EN 13556: ROPS

Botanical name: Robinia pseudoacacia

German: Akazie, Akazie natur, Akazie gedämpft, Robinie gedämpft, Falsche Akazie, Gemeiner Schotendorn

English: Bastard Acacia, False Acacia, Black Locust

French: Robinier, Faux Acacia

Italian: Robinia, Cascia, Gaggia

Spanish: Acacia de dos púas, Acacia de flor blanca, Acacia de los paseos, Acacia falsa, falsa Acacia, falso Aromo, Robinia

Portuguese: Acácia bastarda, falsa Acácia

Dutch: Robinia

Technical wood properties

Weight fresh/green: 800 - 950 kg/m³

Density air dry (12-15% u): 720 - 850 kg/m³

Tensile strength: 120 - 148 N/mm²

Compressive strength: 58 - 86 N/mm²

Flexural strength: 118 - 167 N/mm²

Shear strength: 16 - 20 N/mm²

Hardness according to Brinell BII: 67 - 88 N/mm²

Hardness according to Brinell BØ: 25 - 43 N/mm²

Differential shrinkage (radial): 0.20 - 0.26%

Differential shrinkage (tangential): 0.32 - 0.38%

Natural durability (DIN-EN 350-2): 1-2, very durable to durable

Values of the technical properties of a wood species refer to a wood moisture content of u ¯12% to 15%. Data without guarantee.

Occurrence

The robinia originates from the east of the USA. Today the tree is naturalised practically worldwide. The robinia tree is often cultivated in plantations.

Trunk and bark

Robinia grows very quickly and up to 30 m high. The bark is thin and early forms a deep reticulated bark of a grey-brown colour.

Characteristics and wood colour

The sapwood of Robinia is rather narrow and yellowish, while the heartwood is greenish-yellow in colour. The wood colour darkens to a golden brown tone after a short time. Robinia wood is often steamed to a mocha-brown shade. the annual rings are clearly visible and delineated.

Replacement woods

Ash, hickory, white oak or tropical woods such as afzelia, bilinga, makoré, teak

Literature

- *Wood Atlas | 6th edition in 2006 | Rudi Wagenführ*
- *Wood science volume 1-3 | 1982 | Hans Heinrich Bosshard*
- *Properties and core sizes of wood species | 1989 | Jürgen Sell / Lignum Switzerland*

Specifications

Category	Veneers
Product group	Veneers sliced
Thicknesses	0.56 mm
Weight kg/m2	0.400
Specie	Steamed Black Locust
Botanical name	Robinia pseudoacacia
Wood type	Hardwood
Main occurrence	Europe North America
Wood origin	Austria Switzerland Hungary
Manufacturing/origin	Austria
Certification	not certified
Colour	brown
Hue	medium colour
Use	doors wood goods of all kinds parquet production
Customs tariff number	44089000
Packaging	in bundle, approx. 24-32 sheets
Items on stock	yes
Date of delivery	approx. 3 - 6 working days
Postal shipping	nein

Documents



Prospekt Furniere & Massivholz



Produktblatt Furnier-Imager



Produktblatt mtextur



Holzdeklaration
