



Bouls Utile 60 mm

Item No. 02-000539



Description

The drying process gives the initially pinkish brown to light red wood an intense reddish brown colour. The pronounced alternating twisted growth gives the wood beautiful glossy stripes, which often run very narrowly and evenly. Numerous mirrors on the radial surfaces further enliven the wood's appearance.

Trade names and other names

German: Sapeli
English: Sapele
French: Sapelli
Italian: Sapelli
Spanish: n.a.
Dutch: n.a.
Portuguese: n.a.
Arabic: n.a.
Chinese: 非洲花梨

Available thicknesses

30, 40, 52, 60, 70, 80 mm, other thicknesses on request.

Occurrence

Sapelli mahogany is widespread in West and Central Africa.

Trunk and bark

The tree is straight-shafted and cylindrical, up to 30 in knot-free; ring peeling is possible.



Characteristics and wood colour

Coloured and on the surface only slightly porous wood with a particularly decorative appearance due to structure, colouring and gloss. Sapwood 3-8 cm wide, light grey to yellowish, heartwood initially pink to light red and clearly separated from the sapwood; after drying often darkens to deep reddish brown; on the whole less prone to colour variations than other species of the same genus.

Specifications

Category	Lumber
Product group	Unedged lumber
Thicknesses	60 mm
Weight kg/m3	640.000
Specie	Utile
Botanical name	Entandrophragma utile
Wood type	Hardwood
Main occurrence	Africa
Wood origin	Cameroon Congo, Dem. Rep.
Certification	not certified FSC®100%
Colour	dark red
Hue	medium colour
Use	Boat and ship building construction wood Carving and turnery work
Surface structure	rough-cut
Humidity	10% ± 2%
Customs tariff number	44072920
Packaging	loosely
Items on stock	yes
Date of delivery	approx. 3 - 6 working days
Postal shipping	nein

Documents

 Prospekt Furniere & Massivholz
 Holzdeklaration