Atlas Holz AG



Bouls Tulipwood 50 mm

Item No. 02-001035



Description

The tulip tree is widespread in the south-eastern part of the USA, but also cultivated and grown in Europe. The texture is medium fine and uniform, the structure usually straight grained. The sapwood is narrow and almost white and stands out against the light or dark yellow, greenish, or reddish brown heartwood. The annual rings are not visible to the naked eye.

Trade names and other names

German: Tulpenbaum English: American whitewood, Tulip poplar French: Tulpier Italian: Tulipifero Spanish: n.d. Dutch: Tulpenboomhout Portuguese: n.a. Arabic: Shang es zanbag Chinese: n.a.

Available thicknesses

40, 50, 60 mm, other thicknesses on request

Occurrence

Widespread in the south-eastern part of the USA, cultivated and grown in other countries and in Europe.

Trunk and bark

In Europe, the tulip tree usually grows from 5 to 8m high, in the USA where it comes from, the tulip tree can reach a height of about 60m and a diameter of up to 2m. The trunk is very straight and well grown and branch-free up to about 30m. The bark is smooth, soft and ash-grey when young and deeply fissured when old. Tulip tree bark has a somewhat bitter but aromatic taste and is used medicinally.

Characteristics and wood colour

Annual rings are not visible to the naked eye. The structure is usually straight grained, the texture medium fine and even. The sapwood of the tulip tree is narrow and almost white, often lighter striped in colour and stands out from the heartwood. The heartwood varies between light and dark yellow, greenish or reddish brown.

Specifications

Category	Lumber
Product group	Unedged lumber
Thicknesses	50 mm
Weight kg/m3	430.000
Specie	Tuliptree / Yellow Poplar
Botanical name	Liriodendron tulipifera
Wood type	Hardwood
Main occurrence	North America
Wood origin	Canada USA
Certification	not certified
Colour	white
Hue	clear
Hue Use	clear interior Carving and turnery work
Use	interior Carving and turnery work
Use Surface structure	interior Carving and turnery work rough-cut
Use Surface structure Humidity	interior Carving and turnery work rough-cut 10% ± 2%
Use Surface structure Humidity Customs tariff number	interior Carving and turnery work rough-cut 10% ± 2% 44079910
Use Surface structure Humidity Customs tariff number Packaging	interior Carving and turnery work rough-cut 10% ± 2% 44079910 loosely

Documents

Prospekt Furniere & Massivholz

181 人

Holzdeklaration