



## Substructure Larch glued laminated timber | four sided smooth

Item No. 10-000095



## Description

Larch has always been an excellent timber, which is used for interior finishing, but especially for exterior use. Thanks to the high resin content of larch wood, it is avoided by vermin. Larch wood comes from Central and Northern Europe, but also from Russia and Siberia. The durability class is 3-4, i.e. it is moderately durable. The heartwood is yellow-red to red-brown. The larch substructure comes from legal and sustainable logging. The substructure slats are untreated, glued in several layers, finger-jointed (similar to glulam) and planed on 4 sides.

### Grading

The substructures (UK) are generally available in a standard quality. Occasionally, sub-structures with damage, cracks, areas that have not been planed out cleanly and drop-out knots may occur. The goods are not re-sorted and therefore contain all grades from A to C. In some cases, the individual substructure battens cannot be used in their full length and must be cut to a healthy length on site. We recommend that you plan for at least 10% of the goods as a reserve or offcut.

### Assembly




The installation must be carried out professionally, i.e. the maximum distance of the substructure must not exceed approx. 40-45 cm. A slope of at least 2% must be maintained in the longitudinal direction of the boards. The decking boards must be well ventilated. Waterlogging must be prevented by structural wood protection such as rubber or plastic underlays. Please use only fastening materials made of stainless steel (V2A or V4A) for installation. Simple fastening materials that are only galvanised react with the ingredients of the wood and lead to unsightly, usually dark discolouration. If the screws are visible, the holes must be pre-drilled to avoid cracks and splintering due to the tension in the wood. Treat the decking boards with an end-grain wood preservative at the ends to prevent drying-related cracks at the board ends.

## Specifications

Category	Garden
Product group	Substructure
Lengths	5000 mm
Widths	70 mm
Thicknesses	40 mm
Weight kg/piece	600.000

Specie	Knotty Siberian Larch
Botanical name	Larix sibirica
Wood type	Softwood
Wood origin	Europe
Manufacturing/origin	Europe
Certification	not certified
Durability class	3 / moderately permanent, 10 to 15 years   4 / little durable, 5 to 10 years
Construction	multi-layer construction
Wood bleeding	light
Customs tariff number	44071990
Packaging	loosely
Items on stock	yes
Date of delivery	approx. 3 - 6 working days
Postal shipping	nein

## Documents

	Prospekt Terrassendielen
	Prospekt Holz im Garten
	Tipps und Tricks für Terrassen- und Fassadenbau
	Terrassenmontage Merkblatt