



## Bouls Alder steamed 32 mm

Item No. 02-000241



---

## Description

The alder is typical for riparian forests and banks of slow-flowing streams. The wood is discreetly grained. Tangentially decorative drawings in the wood as well as radially delicate stripes are produced by faintly marked annual ring boundaries. Characteristic of this reddish-white, reddish-yellow to reddish-brown wood are frequently occurring pith flecks.

## Trade names and other names

German: Alder steamed

English: Black alder, Common alder

French: Aulne commun, Aulne noir, Vergne

Italian: Alno ontana, Ontano nero

Spanish: Alano nigro, Aliso, Ameneriro

Dutch: Elzen

Portuguese: Amieiro

Arabic: Hhamarayah

Chinese: 桤木

## Available thicknesses

32, 40, 50, 52, 60 mm, other thicknesses on request.

## Occurrence

The home of alder stretches across Europe to Siberia, the Near East and Northwest Africa.

# Trunk and bark

The alder tree reaches heights of up to 20m and more, with the trunk being free of branches up to about 15m. Diameters go up to 1m, but are usually smaller and only up to about 0.5m. The bark is greenish in young alder, later changing to dark brown and becoming quite cracked.



# Characteristics and wood colour

The annual rings are of different widths and the false pith rays appear as mirrors in radial section and as darker longitudinal stripes in tangential section. Pore arrangement scattered and small. The sapwood and heartwood are indistinguishable in alder. The wood is reddish-white to yellow-red, but darkens quickly when exposed to light and air. Alder wood is often used as an imitation for precious woods.

# Specifications

Category	Lumber
Product group	Unedged lumber
Thicknesses	32 mm
Weight kg/m3	600.000
Specie	Alder steamed
Botanical name	Alnus glutinosa
Wood type	Hardwood
Main occurrence	Europe
Wood origin	Austria   Switzerland   Hungary
Certification	not certified   FSC®100%
Colour	red
Hue	clear
Use	interior   Carving and turnery work   wood goods of all kinds
Surface structure	rough-cut
Humidity	10% ± 2%
Customs tariff number	44079910
Packaging	loosely
Items on stock	yes
Date of delivery	approx. 3 - 6 working days
Postal shipping	nein

# Documents

	Prospekt Furniere & Massivholz
	Holzdeklaration