



1-layer solid wood panel European Oak | A/B | continuous lamellas

Item No. 06-001137



Description

The single-layer stair tread panels with continuous lamellas are produced in standard quality A/B and glued D3 according to DIN/EN204 without formaldehyde. The lamella width usually varies from approx. 40 to 80 mm depending on availability and wood species. The boards are individually laminated. Special formats and finishes are available on request from a minimum of 20 boards.

Quality A: practically free of defects, basically without knots, without heartwood, with a small amount of sapwood, especially in oak, cherry and walnut.

Quality B: with intergrown knots, ingrowths, sapwood and small defects.

Storage

Solid wood panels may only be stored in closed, dry and not too cold rooms. The boards must not be stored near heaters, damp walls, open doors or windows and must be protected from direct sunlight. The ideal storage temperature is approx. 20 °C at a relative humidity of 45 to 55 % without large temperature fluctuations. The solid wood panels need a longer time to adjust after a large temperature change. The boards should always be stored lying down.

Transport

If possible, the boards should be transported lying down. When securing the load, always fasten the tensioning straps in line with the squared lumber so that no deformation or breakage of the boards occurs when lashing the straps.

The boards should not be left on the loading bridge of the truck overnight or over the weekend, especially in case of strong temperature fluctuations or in the winter months.

Processing

The moisture content of the boards must be measured before and after processing. The ideal wood moisture content is $8\% \pm 2\%$. The room climate in the workshop should have an air temperature of approx. 20° and a relative humidity of 35 to 55% during processing.

We recommend that you process the solid wood panels promptly in one go, i.e. ripping, routing, sleeping and lacquering. This reduces the risk of warping, as the boards can practically not absorb any moisture. The panels must also be painted over the entire surface on the front side to prevent moisture from penetrating.

In order to avoid joints and possible cracks, we recommend blocking off the surfaces with veneer, MDF or paper. Wood suffers especially during the heating period if the room climate is unhealthily too dry. Please always check your room climate and humidify if necessary.

If you do not follow these instructions, open glue joints or even warping or cracking of the wood may occur. The processing and storage instructions must be observed especially for beech wood. This hardwood reacts very strongly to changes in humidity.

Specifications

| Category | Panels |
|------------------------|---|
| Product group | 1-layer solid wood panels standard |
| Lengths | 3200 mm |
| Widths | 650 mm |
| Thicknesses | 40 mm |
| Tolerance of thickness | ± 0.5 mm |
| Specie | European Oak |
| Botanical name | Quercus robur/Quercus petraea |
| Wood type | Hardwood |
| Wood origin | Croatia Poland Slovenia Hungary |
| Manufacturing/origin | Croatia Poland Slovenia |
| Certification | not certified |
| Construction | 1-layer construction |
| Quality front | A |
| Quality back | B |
| Lamella | continuous |
| Slat Width | from 40 to 70 mm, depending on availability |
| Surface structure | sanded, grit 80-120 |
| Surface treatment | untreated |
| Humidity | $8\% \pm 2\%$ |
| Gluing | D3 nach DIN/EN204 |
| Customs tariff number | 44219900 |
| Packaging | individually foiled |
| Items on stock | no |
| Date of delivery | in stock approx. 4 to 8 business days, from production approx. 2 to 6 weeks |

| | |
|----------------------|------|
| Postal shipping | nein |
| Unvisible in Webshop | ja |

Documents



Prospekt Massivholzplatten
