



3-layer panel reclaimed Sp/Fi/Pi type 2A | chopped | brushed

Item No. 06-001520



Description

The cover slats in old spruce/fir/pine type 2A are cut from old beams, lightly steamed and machine-chopped. They have a beautiful worm pattern with slight cracks. By hand, all slats are patched with real wood, which ensures a natural and harmonious appearance.

Available lengths

2200, 2560, 3000, 3500 und 4000 mm

Structure

Thickness 19 mm = 6.5/6.5/6.5 mm, Thickness 27 mm = 6.5/15.0/6.5 mm, Thickness 42 mm = 6.5/30.0/6.5 mm

Middle layer

The middle layer of the 3-layer panels is made of "new spruce". On customer request, we process the middle layers with special properties (e.g. fire protection or lightweight construction).

Back side

The use of old wood (2nd patina) on the reverse side of our three-layer panels ensures that the panels remain quieter and more stable than panels made with new wood. The back is sanded as standard and not patched.

Range of application

The boards offer a variety of uses such as wall panelling, furniture, doors, wooden flooring.

Optics: patching

Cracks or knotholes are patched by hand using only real wood. The result is a visually harmonious and natural old wood surface. We do not use silicone or similar chemical fillers for patching, as these only spoil the look and feel of a surface. Chemically repaired areas attract dust and are difficult to clean.

Optics: grading

Only trained and motivated personnel with sufficient experience create old wood surfaces with a unique character. A harmonious appearance and consistent quality for each panel is particularly important. Precise guidelines and a great deal of intuition for a balanced grading prevent panel images with a "zebra look", which disturb the

overall picture and make it appear unsettled.

Optics: glue joints

The glue joints are always pressed together and form a visually uniform panel appearance. In the case of inferior industrial production, open glue joints not only impair the appearance, but also the load-bearing capacity and service life of a three-layer board.

Optics: pests

Only an infestation of the knock beetle beautifies the old wood and gives the surface a unique appearance. We do not use any raw wood for our three-layer boards that has been destroyed by the house longhorn beetle or by white, brown and blue rot.

Standards and certification

The following standards apply to waste wood products:

- Fire resistance EN ISO 9239-1 and/or EN 13501-1
- formaldehyde: EN 717-1
- pressure shear test: EN 13354
- gap test: DIN 68 705-2
- CE marking for non-load-bearing construction products according to EN 13986
- Declaration of performance in spruce and oak available

Specifications

| Category | Reclaimed Wood Panels |
|------------------------|---|
| Product group | 3-layer solid wood panels |
| Lengths | 3500 mm |
| Widths | 1025 mm |
| Thicknesses | 19 mm |
| Tolerance of thickness | ± 2.0 mm |
| Specie | Reclaimed Spruce steamed |
| Botanical name | Picea abies/Abies alba/Pinus sylvestris |
| Wood type | Softwood |
| Wood origin | Central Europe |
| Manufacturing/origin | Austria |
| Certification | not certified CE label |
| Construction | 3-layer construction |
| Quality front | visible |
| Quality back | not visible |
| Lamella | continuous |
| Slat Width | mixed from 80 mm and wider |
| Surface structure | maschine chopped and slightly brushed |
| Surface treatment | untreated |
| Humidity | 8% ± 2% |
| Gluing | D3 nach DIN/EN204 |
| Customs tariff number | 44219900 |
| Packaging | loosely |
| Items on stock | no |

| | |
|------------------|---------------------|
| Date of delivery | approx. 3 - 6 weeks |
| Postal shipping | nein |

Documents



Prospekt Altholz



Prospekt Altholtoberflächen
