

1-layer solid wood panel European Cherry | A/B | continuous lamellas

Item No. 06-003086



Description

The 1-layer boards with continuous lamellas are produced in standard quality A/B and glued D3 according to DIN/EN204 without formaldehyde. The boards are individually foiled. On request, special formats and processing are possible from a minimum of 20 boards.

Quality A: practically free of defects, basically without knots, without heartwood, with a small amount of sapwood, especially in oak, cherry and walnut. Quality B: with intergrown knots, ingrowths, sapwood and small defects.

Storage

Solid wood panels may only be stored in closed, dry and not too cold rooms. The boards must not be stored near heaters, damp walls, open doors or windows and must be protected from direct sunlight. The ideal storage temperature is approx. 20 °C at a relative humidity of 45 to 55 % without large temperature fluctuations. The solid wood panels need a longer time to adjust after a large temperature change. The boards should always be stored lying down.

Transport

If possible, the boards should be transported lying down. When securing the load, always fasten the tensioning straps in line with the squared lumber so that no deformation or breakage of the boards occurs when lashing the straps.

The boards should not be left on the loading bridge of the truck overnight or over the weekend, especially in case of strong temperature fluctuations or in the winter

Processing

The moisture content of the boards must be measured before and after processing. The ideal wood moisture content is $8\% \pm 2\%$. The room climate in the workshop should have an air temperature of approx. 20° and a relative humidity of 35 to 55% during processing.

We recommend that you process the solid wood panels promptly in one go, i.e. ripping, routing, sleeping and lacquering. This reduces the risk of warping, as the boards can practically not absorb any moisture. The panels must also be painted over the entire surface on the front side to prevent moisture from penetrating.

In order to avoid joints and possible cracks, we recommend blocking off the surfaces with veneer, MDF or paper. Wood suffers especially during the heating period if the room climate is unhealthily too dry. Please always check your room climate and humidify if necessary.

If you do not follow these instructions, open glue joints or even warping or cracking of the wood may occur. The processing and storage instructions must be observed especially for beech wood. This hardwood reacts very strongly to changes in humidity.

Specifications

| Product group 1-layer solid wood panels Lengths 2600 mm Widths 1250 mm Thicknesses 30 mm Tolerance of thickness ± 0.5 mm | standard |
|--|----------|
| Widths 1250 mm Thicknesses 30 mm | |
| Thicknesses 30 mm | |
| | |
| Talerance of thickness +0.5 mm | |
| | |
| Weight kg/piece 74.100 | |
| Specie European Cherry unsteam | ed |
| Botanical name Prunus avium | |
| Wood type Hardwood | |
| Wood origin Central Europe | |
| Manufacturing/origin Poland | |
| Certification not certified | |
| Construction 1-layer construction | |
| Quality front AB | |
| Quality back B | |
| Lamella continuous | |
| Slat Width from 40 mm can be fixed o | rfalling |
| Surface structure sanded, grit 80-120 | |
| Surface treatment untreated | |
| Humidity 8%±2% | |
| Gluing D3 nach DIN/EN204 | |
| Customs tariff number 44219900 | |

| Packaging | individually foiled |
|------------------|---|
| Items on stock | no |
| Date of delivery | in stock approx. 4 to 8 business days, from production approx. 2 to 6 weeks |
| Postal shipping | nein |

Documents

자

Prospekt Massivholzplatten